

Applications

- Encapsulation
- Hot melt adhesives
- Photovoltaic Cells

Characteristics

- Good balance of adhesion and COF
- Excellent light transmission characteristics

Property	Value	Unit	Method
Melt Index, MI ₂	40	g/10min	D 1238
Density	0.954	g/cm ³	
Vinyl Acetate Content	28	%	
Vicat Softening Point	93	°F	D 1525
Tensile Strength at Break	900	psi	D 638
Elongation at Break	900	%	D 638
Tensile Modulus	1200	psi	D 638
Hardness, Shore A	66	g	D 2240
Hardness, Shore D	13	%	D 2240

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net