

Extrusion Coating

Applications

- Laminations
- Cast film
- Compounding

Characteristics

- Exceptional clarity
- Exceptional toughness
- Good drawdown

Property	Value	Unit	Method
Melt Index, M_{12}	8.0	g/10min	D 1238
Density	0.930	g/cm ³	D 1505
Vinyl Acetate Content	9	%	
Vicat Softening Point	165	°F	D 1525
Peak Melting Temperature	207	°F	D 3417
Durometer Hardness, Shore D	48		D 2240
Tensile Strength at Break	1760	psi	D 638
Tensile Strength at Yield	1030	psi	D 638
Elongation at Break	500	%	D 638
Tensile Modulus, 1% Secant	14000	psi	D 882

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net