

Compounding

Applications

- Compounding
- Extrusion compounds
- Molding compounds
- Injection molding

Property	Value	Unit	Method
Melt Index, MI ₂	23	g/10min	D 1238
Density	0.940	g/cm ³	
Vinyl Acetate Content	18.5	%	
Peak Melting Point	185	°F	
Vicat Softening Point	131	°F	D 1525
Tensile Strength at Yield	660	psi	D 638
Tensile Strength at Break	1100	psi	D 638
Elongation at Yield	150	%	D 638
Elongation at Break	> 800	%	D 638
Secant Modulus, 1%	7500	psi	D 790
Hardness Shore A	75		D 2240
Hardness Shore D	32		D 2240
Dart Impact, -40°F	18	ft-lb	D 3763
Dart Impact, 73°F	10	ft-lb	D 3763

Additives: No Slip, No Antiblock

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

(Domestic) 1-800 417-4605
(International) +1-646-790-7200

www.globalplastics.net