

Film Extrusion

Applications

- Adhesive applications

Property	Value	Unit	Method
Melt Index, MI ₂	150	g/10min	D 1238
Density	0.945	g/cm ³	D 1505
Vinyl Acetate Content	28	%	
DSC Melt Temperature	154	°F	D 3418
Ring & Ball Softening Point	196	°F	E 28
Tensile Strength at Break	580	psi	D 638
Elongation at Break	810	%	D 638
Flexural Modulus (1% Secant)	2180	psi	D 790
Hardness Shore A	73		D 2240
Hardness Shore D	19		D 2240

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net