

### Extrusion Coating

#### Applications

- High clarity applications
- Extrusion coating applications

#### Characteristics

- Excellent heat sealability
- Exceptional clarity
- Good balance of drawability and neck-in

Property	Value	Unit	Method
Melt Index, $M_{12}$	18	g/10min	D 1238
Density	0.939	g/cm <sup>3</sup>	
Vinyl Acetate Content	26	%	
Vicat Softening Point	129	°F	D 1525
Tensile Strength at Break MD/TD	3100/2200	psi	D 882
Elongation at Break MD/TD	530/810	%	D 882
Secant Modulus, 1% Secant MD/TD	7400/8000	psi	D 882
Elmendorf Tear Strength MD/TD	240/330	psi	D 1922
Dart Drop Impact	90	g	D 1709
Haze	0,9	%	D 1003
Gloss (45°)	89		D 2457

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

**GLOBAL PLASTICS LP**

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

[www.globalplastics.net](http://www.globalplastics.net)