

Blow Molding

Applications

- Milk Containers
- Food Packaging
- Water Bottles
- Juice Containers

Characteristics

- Slurry Loop
- Excellent Stiffness
- Low Taste and Odor
- Good Rigidity

Regulatory - This material complies with FDA regulations in 21 CFR, section 177.1520.

Property	Value	Unit	Method
Melt Index	0.7	g/10min	D 1238
Density	0.964	g/cc	D 1505
Tensile Strength at Yield	4500	psi	D 638
Elongation at Break	> 300	%	D 638
Flexural Modulus	240000	psi	D 790
ESCR, Condition B, F ₅₀	10	hours	D 1693
Brittleness Temperature, F ₅₀	< -180	°F	D 746

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net