

Blow Molding and Compounding

Applications

- Compounding
- Containers
- Blow molding applications

Characteristics

- Unstabilized HDPE copolymer
- Can be compounded to include stabilizers, fillers and colorants prior to processing in order to meet specific requirements of the molding applications

This product is not intended for and should never be used in medical related applications.

Property	Value	Unit	Method
Melt Index, MI ₂	.35	g/10min	D 1238
Density	0.953	g/cm ³	D 4883

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net