StarResin[™]

PRODUCT DATA SHEET

Autoclave

Applications	Characteristics		
 Produce bags 	Outstanding haze and gloss		
 High clarity films 	Good strength		
 Bakery bags 	Good heat sealability		
 Retail packaging 	 Excellent processability 		
Property	Value	e Unit	Method
Melt Index, MI ₂	2.0	g/10)min D 1238
Density	0.923	3 gm/o	cc D 1505
Haze	8.0	%	D 1003
Gloss (45°)	90		D 2457
Dart Drop Impact	110	gm/i	mil D 1709
Elmendorf Tear Strength MD	'TD 330/	190 gm/i	mil D 1922
Tensile Strength at Break MD	/TD 3650	/2900 psi	D 882
Elongation at Break MD/TD		630 %	D 882
Secant Modulus, 1% Secant MD/TD		0/29000 psi	D 882

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GL BAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014 (Domestic) 1-800 417-4605 (International) +1-646-790-7200 www.globalplastics.net