

PRODUCT DATA SHEET

## Nylon 6/6 33% Glass Filled Repro Black

## **Injection Molding**

**Features** 

**Form** 

Good mold ability

Pellets

Value	Unit	Method
1.35-1.4	g/cc	D 792
21000-23000	psi	D 638
2	%	D 638
900-950	ksi	D 790
1.8-2.2	ft-lb/in	D 256
475	°F	D 648
105	R	D 785
	1.35-1.4 21000-23000 2 900-950 1.8-2.2 475	1.35-1.4 g/cc 21000-23000 psi 2 % 900-950 ksi 1.8-2.2 ft-lb/in 475 °F

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.



21 Downing Street Front 1 New York, NY 10014 (Domestic) 1-800 417-4605 (International) +1-646-790-7200 www.globalplastics.net