

Extrusion

Applications

- Bulk Continuous Filaments
- Bulk Filament
- Continuous Filaments
- Staple Fibers
- Carpet Applications
- Upholstery Applications

Property	Value	Unit	Test
Melt Index, (230°C/2.16 kg)	25	g/10 min	ASTM D 1238
Density	0.900	g/cm ³	ISO 1183
Flexural Modulus	1700	MPa	ISO 178
Tensile Stress at Break	36	MPa	ISO 527
Tensile Strain at Break	> 50	%	ISO 527
Tensile Strain at Yield	10	%	ISO 527
Izod Notched	2.2	KJ/m ²	ASTM D 256
Heat Deflection Temperature	89	°C	ISO 75B
Vicat Softening Temperature	155	°C	ISO 306

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net