

Extrusion

Applications

- Pipe
- Profile
- Sash

Product Description: PVC K67 homopolymer made by suspension polymerization can be applied to rigid extrusion process like sash or pipe. Products made from this resin have excellent mechanical properties and bright color.

Property	Value	Unit	Method
Degree of polymerization, 30°C	1030±30	-	JIS K6721-77
K-Value	66	-	DIN 53726
Particle size distribution, 45 Mesh	Max 0.5	%	ASTM D1921
Bulk density	0.595±0.025	g/cm ³	ASTM D 1895-90
Real density, 23°C	1.4		ASTM D 792
Heat Loss	Max 0.2	%	ASTM D 3030-95

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net